

T.P. No.	Test Temp. (°C)	D0 (mm)	D (mm)	L0 (mm)	L (mm)	0.2% offset Y.S (N/mm <sup>2</sup> )	Tensile Strength (N/mm <sup>2</sup> )	Elong- ation (%)	Reduction of Area (%)	Fracture Location
Spec. (JIS H 4650 TAB6400H)						825	895	10	25	
1	RT	6.02	4.48	31.85	36.15	971	1045	13.5	45	A
2		6.02	4.51	32.18	36.55	968	1047	13.6	44	A
3		6.01	4.51	31.83	36.21	975	1040	13.8	44	A
4	200	6.02	4.22	31.88	36.20	749	830	13.6	51	A
5		6.01	4.21	31.82	36.30	757	843	14.1	51	A
6		6.02	4.28	31.98	36.30	753	834	13.5	49	A
7	400	6.00	3.98	31.83	36.27	653	739	13.9	56	A
8		6.02	4.07	31.90	36.42	649	730	14.2	54	A
9		6.02	4.00	31.97	36.59	651	723	14.5	56	A
13	500	6.02	2.59	31.88	40.68	534	593	27.6	81	B
14		6.02	2.42	31.94	41.18	536	592	28.9	84	B
15		6.02	2.44	31.83	40.49	534	589	27.2	84	B
10	600	6.02	0.32	31.91	49.71	339	372	55.8	100	B
11		6.02	0.31	31.89	47.08	334	365	47.6	100	B
12		6.02	0.33	31.90	45.40	335	369	29.7	100	B
16		6.02	0.3	31.95	40.27	336	370	20.7	100	C