




Material:FC300



T.P. No.	Test Temp. (°C)	Absorbed Energy (J)	Average (J)	Lateral Expansion (mm)	Shear Fracture (%)
FC300-4	100	3.7	3.8	0.05	0
FC300-5		4.0		0.02	0
FC300-6		3.7		0.01	0
FC300-7	20	3.1	3.0	0.02	0
FC300-8		3.1		0.01	0
FC300-9		2.8		0.03	0
FC300-1	0	3.1	3.1	0.01	0
FC300-2		3.1		0.05	0
FC300-3		3.1		0.01	0